

POLYCARBONATE PROFILE

Specifications	Value	Test Method
Density (gr/cm ³)	1,2	ISO 1183
Water Absorption (%)	0.35	ISO 62
Tensile Modulus (Mpa)	2300	ISO 527
Using Temperatures °C	-40/+120	
Tensile Strenght (Mpa)	63	ASTM D 638
Vicat Softening Temperature °C	145	ISO 306

PRODUCT FEATURES

Range in mm	Variable from 4-16 mm (Regards to multiwall PC sheets thickness)
Profile Shape	H and U Profile
Length mm	Variable (on request)
Weight g/m (Vary depend on profile shape and thickness)	H Profile= 80-175 U Profile= 40-85